




## FOR PROFESSIONAL USE ONLY

<b>Quick Ref:</b>	<b>2K Matting Agent</b>
-------------------	-------------------------

  	Various	<p><b>Description:</b> Matting agent formulated to reduce the gloss level of Superthane 2K Topcoats. The target use for this product is refinishing and refurbish of existing vehicles and the painting of newly build commercial vehicles and trailers. The EU VOC limit for this product (product category: IIB.E) in ready to use form is max 840 g/litre. The VOC content of this product in ready to use form is max 640 g/litre</p>																																			
	CONSULT TECHNICAL DATA SHEET BEFORE USE	<p><b>Product and Additives:</b> 2K Matting Agent</p>																																			
	Wear suitable protection	<p><b>Basic Raw Materials:</b> 2K Matting Agent                      Silica matting agent, acrylic resin, solvents, additives</p>																																			
		<p><b>To be used in:</b></p> <ul style="list-style-type: none"> <li>▪ Superthane 2K S80 Topcoat</li> <li>▪ Superthane 2K S1050 Topcoat</li> <li>▪ Superthane 2K S2000 Topcoat</li> </ul>																																			
		<p><b>Replacement method:</b> 2K Matting Agent can be used by (partly) replacing 2K Binder in the color formulas. Mixing ratio on weight:</p> <table border="1" data-bbox="550 1146 1284 1406"> <thead> <tr> <th colspan="2"></th> <th>Semi gloss 40-60 GU</th> <th>Matt 10-20 GU</th> </tr> </thead> <tbody> <tr> <td rowspan="3">S80</td> <td>2K Tinter</td> <td>40%</td> <td>40%</td> </tr> <tr> <td>S80 Binder</td> <td>20 - 30%</td> <td>0 - 15%</td> </tr> <tr> <td>2K Matting agent</td> <td>30 - 40%</td> <td>45 - 60%</td> </tr> <tr> <td rowspan="3">S1050 / S2000</td> <td>2K Tinter</td> <td>50%</td> <td>50%</td> </tr> <tr> <td>S1050 / S2000 Binder</td> <td>10 - 20%</td> <td>0 %</td> </tr> <tr> <td>2K Matting agent</td> <td>30 - 40%</td> <td>50 - 75%<sup>*)</sup></td> </tr> </tbody> </table> <p><sup>*)</sup> As S1050 and S2000 topcoat consists of 50% binder, extra binder is needed to matt some colors.</p> <p><b>Adding method:</b> Ready mixed colors can also be matted by adding 2K Matting Agent on weight:</p> <table border="1" data-bbox="550 1599 1284 1720"> <thead> <tr> <th colspan="2"></th> <th>Semi gloss 40-60 GU</th> <th>Matt 10-20 GU</th> </tr> </thead> <tbody> <tr> <td>S80</td> <td></td> <td>90 - 110%</td> <td>120 - 130%</td> </tr> <tr> <td>S1050 / S2000</td> <td></td> <td>70 - 90%</td> <td>100 - 120%</td> </tr> </tbody> </table> <p>Note: Addition of the 2K Matting Agent may cause change in color and opacity.</p> <p>Above mentioned formulas are mixed with the accompanying hardener and thinner to get the ready to spray mixture.</p>			Semi gloss 40-60 GU	Matt 10-20 GU	S80	2K Tinter	40%	40%	S80 Binder	20 - 30%	0 - 15%	2K Matting agent	30 - 40%	45 - 60%	S1050 / S2000	2K Tinter	50%	50%	S1050 / S2000 Binder	10 - 20%	0 %	2K Matting agent	30 - 40%	50 - 75% <sup>*)</sup>			Semi gloss 40-60 GU	Matt 10-20 GU	S80		90 - 110%	120 - 130%	S1050 / S2000		70 - 90%
		Semi gloss 40-60 GU	Matt 10-20 GU																																		
S80	2K Tinter	40%	40%																																		
	S80 Binder	20 - 30%	0 - 15%																																		
	2K Matting agent	30 - 40%	45 - 60%																																		
S1050 / S2000	2K Tinter	50%	50%																																		
	S1050 / S2000 Binder	10 - 20%	0 %																																		
	2K Matting agent	30 - 40%	50 - 75% <sup>*)</sup>																																		
		Semi gloss 40-60 GU	Matt 10-20 GU																																		
S80		90 - 110%	120 - 130%																																		
S1050 / S2000		70 - 90%	100 - 120%																																		

## FOR PROFESSIONAL USE ONLY

		<p><b>Note:</b> Gloss values are strongly dependent on the color. In general (off) white 2K colors need less 2K Matting agent. Addition of matting agent can influence product properties.</p>
		<p><b>Spraying viscosity:</b> See Technical Data Sheets of the products involved.</p>
		<p><b>Application process:</b> See Technical Data Sheets of the products involved.</p>
		<p><b>Cleaning of equipment:</b> Compliant Gunwash</p>
		<p><b>Packaging:</b> 3.75 L can</p>
		<p><b>Colour:</b> Transparent</p>
		<p><b>HEALTH &amp; SAFETY DATA concerning 2K Matting Agent</b></p> <p>For professional use only (see <b>Material Safety Data Sheet</b>) See text on the label of this product. The user of this product is required to comply with the national statutory regulations for health and safety at work and waste disposal.</p>

**AkzoNobel Coatings LTD, Car Refinishes**

**Address:** 136 Milton Park, Abingdon  
Oxfordshire OX14 4SB

**Tel:** 44 (0)1235 862226

**AkzoNobel CR Ireland**

**Address:** Avonbeg Industrial Estate  
Long Mile Road, Dublin 12

**Tel:** 00 353 (0)1450 1344

## FOR PROFESSIONAL USE ONLY

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

**Head Office**

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. [www.masonct.com](http://www.masonct.com)

